


1K WB Polyurethane Dispersion Interior Wall Finish.

PRODUCT DESCRIPTION	AQUAKOTE 201 is a single component, white, waterborne acrylic & polyurethane resin dispersion blend based surface coating containing organic in-film preservative for interior finish.	
WHERE TO USE	Coloured seal coating for internal walls and ceilings. For concrete, bricks, cement based and gypsum substrates, timber, tiles and plastic. Suitable for clean rooms for pharma industry. Also suitable for food and beverage industry, hospitals, healthcare facilities, kitchens. Maintenance layer on existing wall coatings.	
CHARACTERISTICS/ ADVANTAGES	Seamless, glossy, easy clean finish. Easy application. Fast drying, two coats in one working day. Elastomeric, resists cracking and flaking. Good resistance to repeated cleaning regimes using mild detergents and cleaning solutions. Impact, scratch and abrasion resistance. Good covering and hiding power (opacity). Low odour.	
APPEARANCE/ COLOUR	White, Liquid (Can Be Tinted To Any Colour) Single Component	
PACKAGING	5 & 25 kgs.	
STORAGE/ SHELF LIFE	24 months from date of production if stored in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +35°C.	
CHEMICAL BASE	Waterborne acrylic / polyurethane copolymer dispersion.	
DENSITY	1.39 g/cc	
MECHANICAL / PHYSICAL PROPERTIES		
ELONGATION %	> 100%	(ACCORDING TO ISO 527-3)
TENSILE STRENGTH(MPA)	~ 1.5	(ACCORDING TO ISO 527-3)
ADHESION	>1.5 MPA	(ACCORDING TO EN 1542)
APPLICATION DETAILS		
CONSUMPTION/ DOSAGE	90-100 sft per kg per coat depending on the surface porosity. DFT ~ 25 – 30 micron (One coat) (2 coats recommended)	
SUBSTRATE QUALITY	The substrate must be sound and of sufficient compressive Strength (minimum 25 N/mm2) with a minimum pull off strength of 1.5 N/mm2. The substrate must be free of all contaminants such as oil, grease, coatings and surface treatments etc. If in doubt, apply a test area first.	
SUBSTRATE PREPARATION	Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface. Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed. Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate Jemkon products.High spots can be removed by grinding. All dust & loose material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.	
SUBSTRATE TEMPERATURE	+5°C min. / +40°C max.	
MIXING	Single Component. Stir the material to remove any settling.	

JEMKON PVT. LTD

Plot No. 1, Survey No. 795/2, Opp. Mahindra Vehicle Gate No 2, Subhashwadi, Nighoje- Talwade Road, Nighoje, Chakan, Dist. Pune-410501, India.

Tel. : 02135 - 202901. info@jemkon.com www.jemkon.com

1K WB Polyurethane Dispersion Interior Wall Finish.

APPLICATION PROCESS & TOOLS Apply AQUAKOTE 201 onto the primed or putty substrate and spread evenly with Good quality sponge roller, brush or spray to obtain an even layer.

RECOMMENDED UNDERCOATS & OVERCOATS
 Primer : WALL PRIME 31
 Putty : ACRYLIC PUTTY (Optional)
 Sealer :-
 Top coat : AQUAKOTE 201/ AQUAKOTE 301

CLEANING OF TOOLS Clean all tools and application equipment with Clean water immediately after use.

POT LIFE

WAITING TIME/ OVERCOATING	Temperatures	Time
	+25°C	Single Component

APPLIED PRODUCT READY FOR USE	Temperatures	Minimum	Maximum
	+25°C	2 Hours	24 Hours
(Optional) Light sanding advised after maximum time.			

CLEANING/ MAINTENANCE	Temperatures	Minimum	Maximum
	+25°C	24 Hours	-

Times are approximate & will be affected by changing ambient & substrate conditions.

VALUE BASE All technical data stated in this technical Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES The information, and, in particular, the recommendations relating to the application and end-use of Jemkon's products, are given in good faith based on Jemkon's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Jemkon's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Jemkon reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Technical Data Sheet for the product concerned, copies of which will be supplied on request.